

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 63-035765

(43)Date of publication of application : 16.02.1988

(51)Int.Cl.

C23C 14/14

C23C 14/24

(21)Application number : 61-177677

(71)Applicant : KOHJIN CO LTD

(22)Date of filing : 30.07.1986


(72)Inventor : TANOE ATSUSHI
TANADA HIROSUKE

(54) PRODUCTION OF EL ELEMENT

(57)Abstract:

PURPOSE: To produce a dispersion type EL element having a superior light emitting surface which does not cause blackening by forming a thin metallic film as a rear electrode by vacuum deposition at a specified rate on a laminated body consisting of light emitting layer which emits light in an AC electric field and a electrically conductive transparent film as a front electrode.

CONSTITUTION: A light emitting layer 2 consisting of fine particles of a luminous body such as ZnS and a binder having a high dielectric constant is formed on the surface of an electrically conductive transparent film 3 as a front electrode and a rear electrode 1 of a metal such as Al is formed on the layer 2 by vacuum deposition at $\geq 70\text{\AA}/\text{sec}$ rate. The thickness of the electrode 1 is $2,000\text{\AA}$. A dispersion type electroluminescent (EL) light emitting element having superior characteristics as a plane light source is obtd. The light emitting surface of the element does not cause blackening.



LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of